

**BASIC FABRIC**

AURORA

Composition 100%Polyester

Weight 330(+/-)g/m2

Color Fastness to Rubbing  
Dry 4.5      Wet 4


Pilling 4

Abrasion test >15,000

Fire resistance TB117-2013 Compliant



01



02



03



04



05



06



07



08

DUST

Composition      90%Polyester 10%Nylon

Weight            440(+/-)g/m2

Color Fastness to Rubbing  
Dry      Wet  
4.5      4

Pilling            4

Abrasion test      >40,000

Fire resistance    TB117-2013 Compliant




01




02




03



04



05



06



07



08



09



10



11



12

**JASMINE**

|                           |                      |     |
|---------------------------|----------------------|-----|
| Composition               | 100%Polyester        |     |
| Weight                    | 320(+/-)g/m2         |     |
| Color Fastness to Rubbing | Dry                  | Wet |
|                           | 4                    | 4.5 |
| Pilling                   | 3                    |     |
| Abrasion test             | >40,000              |     |
| Fire resistance           | TB117-2013 Compliant |     |



01




02



03




04



05



06



07

FONTAINE

Composition 100%Polyester

Weight 340(+/-)g/m2

Color Fastness to Rubbing  
Dry 4      Wet 4

Pilling 5

Abrasion test >40,000



02



03



07



10



11




14



16




17




19




23



25



27



28



30



31

LAVANDA

Composition 100%Polyester

Weight 460(+/-)g/m2


Color Fastness to Rubbing  
Dry Wet  
4.5 4

Pilling 4

Abrasion test >40,000



13



21




23



24



31



44



45



51




52




55



56



58



60

CRYSTAL

Composition 100%Polyester

Weight 410(+/-)g/m2

Color Fastness to Rubbing  
Dry 4      Wet 3.5

Pilling 4

Abrasion test >40,000




16




19




21



22




23



24



25



28



33

CHANEL

Composition 25%Rayon 80%Polyester

Weight 400(+/-)g/m2

Color Fastness to Rubbing  
Dry      Wet  
4.5      4

Pilling 4

Abrasion test >49,000



01



03



04



05



10




12



13



14



15



17



18

VELVET

Composition 100%Polyester

Weight 410(+/-)g/m2

Color Fastness to Rubbing  
Dry 4      Wet 3.5

Pilling 4


Abrasion test >40,000



02



12



13



15



20



23



26



29



41



43



45



48

**SELECTED FABRIC**

MONTANA

Composition 100%Polyester

Weight 390(+/-)g/m2

Color Fastness to Rubbing  
Dry 4      Wet 4

Pilling 4

Abrasion test >30,000



01




02




03




04



05



06



07



08

**PARADISE**


Composition      100%Polyester

Weight            730(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
4.5            3.5

Pilling            4.5

Abrasion test      >90,000



0225



1047



1048



1051



1056



1058



1060



1061



1064



1067

CINNAMON

Composition      88%Polyester  
                         12%Nylon

Weight            320(+/-)g/m2

Color Fastness to Rubbing  
                         Dry      Wet  
                         4.5      4

Pilling            4

Abrasion test      >40,000



240



241



270



303



310



330



351



354



355



456



550

**IMPORTED FABRIC**

PARIS

Composition      100%polyester

Weight            560(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
5.5            5.5

Pilling            4.5

Abrasion test    >50,000




1802




1804




1808




1809



1811




1812



1813



1815



1816



1817

OLA

Composition      100%polyester

Weight            385(+/-)g/m2


Color Fastness to Rubbing  
Dry            Wet  
5.5            5.5

Pilling            4.5


Abrasion test      >50,000




2311




2312




2319




2320




2323




2324




2327



2334



2335



2342

**BASIC PU LEATHER**

SEATTLE

Composition      100%PU

Weight            700(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
4               3.5

Pilling

Abrasion test      >50,000



01



07



10



11



13



14



16



17



19



219



20



23



25



27



29



32

**SELECTED PU LEATHER**

## SANTORI

Composition 100%PU

Weight 700(+/-)g/m2

Color Fastness to Rubbing  
Dry 4 Wet 3.5

Pilling

Abrasion test >50,000




2383



4001



4076



6015



6267



7174



8049



8110



9006



9030

**REAL LEATHER**

TELA

Composition      Full grain leather

Color Fastness to Rubbing  
Dry      Wet  
4.5      4

Tear Strength      ≥69.1



8825



1152



2096




3506



7722



8805



8833



8933



8972



8990