

# WAXMAN

Inspire your office

## BASIC FABRIC


we collection

AURORA

|                           |                      |     |
|---------------------------|----------------------|-----|
| Composition               | 100%Polyester        |     |
| Weight                    | 330(+/-)g/m2         |     |
| Color Fastness to Rubbing | Dry                  | Wet |
|                           | 4.5                  | 4   |
| Pilling                   | 4                    |     |
| Abrasion test             | >15,000              |     |
| Fire resistance           | TB117-2013 Compliant |     |



01



02



03




04



05



06



07



08

CAMEL

|                           |                      |     |
|---------------------------|----------------------|-----|
| Composition               | 94%Polyester 6%Nylon |     |
| Weight                    | 330(+/-)g/m2         |     |
| Color Fastness to Rubbing | Dry                  | Wet |
|                           | 4                    | 3.5 |
| Pilling                   | 3                    |     |
| Abrasion test             | >20,000              |     |
| Fire resistance           | TB117-2013 Compliant |     |



08



10



14



16



17



23



26



29



31

DUST

|                           |                       |     |
|---------------------------|-----------------------|-----|
| Composition               | 90%Polyester 10%Nylon |     |
| Weight                    | 440(+/-)g/m2          |     |
| Color Fastness to Rubbing | Dry                   | Wet |
|                           | 4.5                   | 4   |
| Pilling                   | 4                     |     |
| Abrasion test             | >40,000               |     |
| Fire resistance           | TB117-2013 Compliant  |     |




01




02




03



04



05



06



07



08



09



10



11



12



JASMINE

|                           |                      |     |
|---------------------------|----------------------|-----|
| Composition               | 100%Polyester        |     |
| Weight                    | 320(+/-)g/m2         |     |
| Color Fastness to Rubbing | Dry                  | Wet |
|                           | 4                    | 4.5 |
| Pilling                   | 3                    |     |
| Abrasion test             | >40,000              |     |
| Fire resistance           | TB117-2013 Compliant |     |



01



02



03



04



05



06



07

# WAXMAN

Inspire your office

## SELECTED FABRIC

we collection

MONTANA

Composition      100%Polyester

Weight            390(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
4               4

Pilling            4

Abrasion test    >30,000



01




02




03




04



05



06



07



08

PARADISE


Composition      100%Polyester

Weight            730(+/-)g/m2


Color Fastness to Rubbing  
Dry            Wet  
4.5            3.5

Pilling            4.5

Abrasion test      >90,000



0225



1047



1048



1051



1056



1058



1060



1061



1064



1067



CINNAMON

Composition     88%Polyester  
                      12%Nylon

Weight            320(+/-)g/m2

Color Fastness to Rubbing  
                      Dry        Wet  
                      4.5        4

Pilling             4

Abrasion test     >40,000



240



241



270



303



310



330



351



354



355



456



550

# WAXMAN

Inspire your office

# IMPORTED FABRIC

we collection

PARIS

Composition      100%polyester

Weight            560(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
5.5            5.5

Pilling            4.5

Abrasion test      >50,000




1802




1804




1808




1809




1811




1812



1813



1815



1816



1817

OLA

Composition      100%polyester

Weight            385(+/-)g/m2


Color Fastness to Rubbing  
Dry            Wet  
5.5            5.5

Pilling            4.5


Abrasion test      >50,000




2311




2312




2319




2320




2323




2324




2327



2334



2335



2342



# WAXMAN

Inspire your office

## PU LEATHER&REAL LEATHER

we collection

GRAND

Composition      100%PU

Weight            770(+/-)g/m2

Color Fastness to Rubbing  
Dry            Wet  
5              5

Pilling

Abrasion test      >250,000

Fire resistance    TB117-2013 Compliant

High scratch resistance

Resistance to hydrolysis (10 years)

Chemical solvents-free



0150



0314



0076



0225



0181



0015



0028



0240



0173



0221



0075



0126

SANTORI

|                           |              |     |
|---------------------------|--------------|-----|
| Composition               | 100%PU       |     |
| Weight                    | 700(+/-)g/m2 |     |
| Color Fastness to Rubbing | Dry          | Wet |
|                           | 4            | 3.5 |
| Pilling                   |              |     |
| Abrasion test             | >50,000      |     |



2383



4001



4076



6015



6267



7174



8049



8110



9006



9030

AUCKLAND

Composition      75%PU  
                         25%PVC

Weight             680(+/-)g/m2

Color Fastness to Rubbing  
                         Dry      Wet  
                         4       3.5

Pilling

Abrasion test       >50,000



8901



8902



8903



8904



8918



8930



TELA

Composition      Full grain leather

Color Fastness to Rubbing

|     |     |
|-----|-----|
| Dry | Wet |
| 4.5 | 4   |

Tear Strength      ≥69.1



0405



1152



2096



3506




7722



8805



8825



8833



8933



8972



8990